

# COMPARISON OF WIRE AND CABLE JACKETING MATERIALS



Many specifiers of technical products look for more detailed information on the products they select for their most critical applications. In an effort to help provide data to make more informed decisions,

Anixter has amassed common values of important material characteristics and summarized them in the following table. These values are approximate and nominal and are only intended to be representative.

Values vary from manufacturer to manufacturer and among product grades. These values are predominantly drawn from industrial tray cable products.

Material Characteristics	CSPE (Hypalon*)	Thermoset CPE	Thermoplastic CPE	PVC
<b>Physical Properties</b>				
Tensile Strength (Psi)	2075	2050	1900	1920
Elongation (%)	375	360	285	350
<b>Aging Characteristics (Air Oven, 121° C, 168 Hours)</b>				
Tensile Strength (% of Original)	97	103	105	98
Elongation (% of Original)	75	79	85	70
<b>Flame Resistance</b>				
20 Min. at 70,000 BTU/Hour	Pass	Pass	Pass	Pass
Cable Tray Fire Test				
<b>Oil Resistance (ASTM #2 Oil)</b>				
Test Temperature (°C)	121	121	100	70
Time of Immersion (Hours)	18	18	18	4
Tensile Strength (% of Original)	90	92	91	87
Elongation (% of Original)	91	94	93	82
<b>Low Temperature Properties</b>				
Cold Bend Test Temperature Passed (° C)	-40	-40	-40	-25
<b>Ozone Resistance</b>				
	Outstanding	Excellent	Excellent	Good
<b>Heat Distortion</b>				
% at 121° C	7-9	7-10	7-9	20 - 40
<b>Limiting Oxygen Index</b>				
Percent Oxygen Required to Sustain Combustion (Atmospheric Air is ~21% Oxygen)	30	31	31	28
<b>Acid Gas Content (%)</b>				
	10	14	14	29% (12% for low-acid gas PVC)
<b>Halogen Content (%)</b>				
	14	14	14	29

\* Hypalon® is no longer available from DuPont.

Anixter Inc. does not manufacture the items described in this publication. All applicable warranties are provided by the manufacturers. Purchasers are requested to determine directly from the manufacturers the applicable product warranties and limitations. Data and suggestions made in the publication are not to be construed as recommendations or authorizations to use any products in violation of any government law or regulation relating to any material or its use.



**For more information or engineering support,  
contact your local Anixter representative at 1.800.ANIXTER.**

**About Anixter:** [anixter.com/aboutus](http://anixter.com/aboutus)  
**Legal Statement:** [anixter.com/legalstatement](http://anixter.com/legalstatement)  
 12T0003X00 © 2013 Anixter Inc. · 05/12

1.800.ANIXTER | [anixter.com](http://anixter.com)



Products. Technology. Services. Delivered Globally.